



Administration

1615 Wisconsin Avenue
 P.O. Box 200
 New Holstein, WI 53061
 Phone: 800-558-5800
 FAX: 920-898-4588

Pavement Marking Equipment Divisions

EAST COAST DIVISION
 79 Montgomery Street
 Montgomery, PA 17752
 Phone: 888-323-2900
 FAX: 570-547-1629

WEST COAST DIVISION
 2490 Ewald S.E.
 Salem, OR 97302
 Phone: 800-253-2909
 FAX: 503-370-4389

APPROXIMATE THERMOPLASTIC YIELDS

Derived quantities are based on 4" wide Hydrocarbon and vary with material specific gravity, application methods, and pavement texture. (Alkyd has approx. 2.5% less yield due to specific gravity of material.)

Spray (Air or Airless) and Ribbon/Extrude

Mils.	Ton/Mile	Lb/Lf	Lf/Ton
60	.528	.200	10,000
90	.792	.300	6,667

Screed/Extrude – Dense Grade Substrata

Mils.	Ton/Mile	Lb/LF	LF/Ton
60	.620	.235	9,000
90	.910	.345	6,250
125	1.173	.444	4,500

Screed/Extrude – Open Grade Substrata

Mils.	Ton/Mile	Lb/LF	LF/Ton
60	.788	.300	7,500
90	.996	.377	5,400
125	1.227	.465	4,300

Word and Symbol Messages (thermoplastic lbs.)

	Sq. ft	60 mil	90 mil	125 mil
STOP	23.5	15.66	23.5	32.63
ONLY	23.0	15.33	23.0	31.94
XING	23.0	15.33	23.0	31.94
RIGHT	29.5	19.66	29.5	40.97
AHEAD	28.5	19.00	28.5	39.58
LEFT	23.0	15.33	23.0	31.94
TURN	23.5	15.66	23.5	32.63
EXIT	23.0	15.33	23.0	31.94
STRAIGHT ARROW	12.5	8.33	12.5	17.35
TURN ARROW	15.5	10.33	15.5	21.53
COMBO ARROW	28.5	19.00	28.5	39.58
RXR	69.0	46.00	69.0	95.76
R	5.7	3.83	5.7	7.98
SCHOOL	35.0	23.33	35.0	48.61